

Test certificate

Type and designation of the material:	Portland cement CEM I 52,5 N Milke® classic
---------------------------------------	--

Origin or manufacturer:	HeidelbergCement AG, Zementwerk Milke / Geseke 59590 Geseke
-------------------------	--

Period of analysis:	yearly average 2010
---------------------	---------------------

Binder test according to DIN 1164/EN 196/EN 197/EN 413/EN 459 and according to internal test instructions:

Grinding fineness residue 630 µm		%	Loss on ignition	1,9	%
Grinding fineness residue 200 µm		%	insoluble residue	0,7	%
Grinding fineness residue 90 µm	0,9	%	SiO ₂	23,4	%
Grinding fineness residue 63 µm		%	Al ₂ O ₃	3,9	%
Fineness	3565	cm ² /g	Fe ₂ O ₃	1,4	%
Spec. gravity		g/cm ³	CaO	64,9	%
Bulk density		kg/dm ³	MgO	0,8	%
Water requirement (NST)	27,0	%	SO ₃	2,8	%
Start of setting	200	Min.	K ₂ O	0,7	%
End of setting	240	Min.	Na ₂ O	0,2	%
False setting - w/b		cm	Cl	< 0,1	%
Water for mortar		%	Brightness	38,1	%
Slump		mm			

Strengths:

Flexural tensile strengths in MPa after				
	1 day	2 days		28 days
	3,6	5,3		9,5

Compressive strengths in MPa after				
	1 day	2 days		28 days
	13,5	25,5		62,2

Remark:

The above-mentioned values are mean values, which are subject to the usual production fluctuations.