

Sub-Base Stone

Sub-base Stone specification



Surface dressing grit

Surface dressing grit 2-4mm clean Quartzite



Laying Course

50mm depth of 2-6mm. single size clean crushed stone to BS EN 13242: 2002



Upper layer

100mm depth 5mm-20mm clean, crushed with well defined edges BS EN 13242:2002



Lower Layer

250mm depth 10 –63mm clean crushed stone with well defined edges. Clean crush stone 10:63