

Surface Dressing

2-4mm (QUARTZITE/GRITSTONE)

1. SCOPE

This specification defines the 2-4mm surface dressing to be applied to the surface of Aquaflow Pavers and subsequently brushed/vibrated between pavers.

2. REFERENCE SPECIFICATIONS

BS EN 1097-2:1998
BS EN 1091-8:2000 Annex A

3. MATERIAL SPECIFICATION

Material supplied shall be referred to as 2-4mm Clean Quartzite and conform to the following sieve analysis and aggregate testing.

SIEVE SIZE	% PASSING
6.3mm	100
5mm	95-100
3.35mm	66-90
1.18mm	0-20
600 microns	0-8
63 microns	0.0-1.5

Aggregate Testing

Los Angeles Coefficient (LA) – Determination of resistance to fragmentation = 20
BS EN 1097-2:1998

Aggregate Abrasion Value- Determination of resistance to abrasion = 2.1
BS EN 1091-8:2000- Annex A

Note: Lower values than those specified signifies better resistance to fragmentation and abrasion and is therefore acceptable.

4. APPROVED SUPPLIER LIST

Where possible suppliers should be registered to BS EN ISO 9000.

Hanson Formpave
Tufthorn Avenue
Coleford
Glos
GL15 6JL

Hanson Building Products
Stewartby
Bedfordshire
MK43 9LZ