

Uniclass L6129	EPIC F122	Aug 09
CI/SfB	Yp4	

Hanson Calcium Aluminate Cement technical data sheet

Hanson Calcium Aluminate Cement (CAC) is manufactured to comply fully with the requirements of BS915 : Part 2 : 1972 (1983) High Aluminate Cements.

The manufacturing process of Hanson Calcium Aluminate Cement clinker resembles that of a metallurgical foundry and the cement is based on calcium aluminates rather than the calcium silicate basis of Portland Cement. This fundamental difference to Portland cements confers upon Hanson CAC properties which makes it suitable for a variety of special applications. It may also be used with PC in carefully controlled proportions for rapid setting applications. The setting properties of Hanson CAC are similar to PC but the strength development is rapid.

Applications

It is vital that Hanson Calcium Aluminate Cement is not used for structural purposes.

However, it may be used in the following applications:

- Rapid strength gain concretes and mortars allowing fast stripping of formwork within six to twenty-four hours.
- Heat resistant and refractory concretes.
- Cold weather concreting where the heat released in the rapid hardening process allows concreting to take place in conditions as low as -10°C.
- Concretes subject to severe chemical attack such as agricultural environments, food industry flooring and drainage systems.
- Mixed with Portland cements, Hanson CAC produces rapid setting concretes and mortars for non-structural applications such as sealing leaks or temporary repairs. Careful selection of proportions is necessary in this application to avoid flash set.

Quality

Hanson CAC is produced using carefully selected limestone and bauxite. The clinker produced in the kiln, which is similar to a metallurgical smelting furnace, is then ground in a conventional cement mill to produce Hanson CAC to BS EN 14647 : Part 2. Strict quality control at each stage of the manufacturing process helps to ensure that a consistent final product is obtained.

For further advise please contact Hanson Cement's Technical Helpline on 0845 722 7853. Such information includes data on fineness, chemical composition, strength, setting time and soundness.

Properties

Strength

Very high early strength is a fundamental characteristic of Hanson CAC. Typical mortar compressive strengths (BS4550) are as follows:

24 hours	minimum 42N/mm ²
3 days	minimum 49N/mm ²

Physical properties

Bulk density	1140kg/m ³
Specific gravity	3.2 – 3.3

Hydraulic properties

Setting time BS EN 14647

	Specification	Typical
Initial (minutes)	Min 120/Max 360	230
Final (minutes)	Max Initial + 120	260

Concrete mix design

Concrete mix design needs to be varied to suit individual circumstances. However, as a general guide cement contents should be at least 400kg/m³ and total water/cement ratio should not exceed 0.40. It is important to ensure adequate curing during the initial hardening stage. This may be achieved by spraying with cold water during the 6 to 24 hour period after placing or by the use of a curing membrane, wet sacking or impervious polythene sheeting to prevent water loss.

It is strongly recommended that trial mixes are carried out prior to commencement of work to ensure that the mix design and material combinations meet the requirements of the specification and method of use.

The following is a guide to the setting characteristics of mixtures

1 part Calcium High Aluminate Cement 3 parts Portland Cement	Rapid set
1 part Calcium High Aluminate Cement 2 parts Portland Cement	Very rapid set
1 part Calcium High Aluminate Cement 1.5 parts Portland Cement	Instant set

Placing and compaction

Mortars and concretes based on Hanson CAC alone can be mixed, placed and compacted using normal techniques for Portland cement mortars and concretes. Mixtures of Hanson CAC and Cem I will set at a rate depending on the particular mix. Special placing and compacting techniques may be required in these cases.

It is strongly recommended that trial mixes are carried out to determine proportions for the desired setting characteristics.

Admixtures and additions

Admixtures which are compatible with Portland cements are normally equally compatible with Hanson CAC. It is recommended however that trial mixes are carried out to determine optimum properties.

Please note: Reference to a Technical Standard number in this leaflet is deemed to include the latest published edition and/or any published amendments issued after the standard's publication, unless a date of issue is quoted in which case reference is to the provisions stated in that edition.

L006(Ci)/08/09/pdf

For further information please contact:

Hanson Cement
Ketton
Stamford
Lincolnshire
PE9 3SX

Technical Helpline:

Tel: 0845 722 7853
(calls charged at local rate)
Fax: 01780 727154
Email: cement.technical.help@hanson.biz

Customer Services:

Tel: 0845 600 1616
(calls charged at local rate)
Fax: 01780 727008
Email: cement.customer.services@hanson.biz