



Victorian Mixture

Victorian Mixture

Manufactured to BS EN 771-1

Brick type

Category II, HD, Clay Masonry Unit

Standard work size

215 x 102.5 x 65mm

Dimensional tolerances

Tolerance category: T2

Range category: R1

Compressive strength

$\geq 35\text{N/mm}^2$

Water absorption

$\leq 11\%$

Durability

F2

Active soluble salts content

S2

Configuration

Vertically Perforated 18-23% voids

Dry weight per brick

2.25kg

Pack size

475

This panel is printed on paper made using ecf from fibres obtained from a sustainable timber source.

DISCLAIMER:

The reproduction of colours and textures is only as accurate as the printing process will allow. Photographic samples should be used when shortlisting products but we advise that an actual sample should be seen before ordering.

Our new on-line **3D Visualiser** brings brick projects to life



Visit www.hanson.com/uk



Hanson
Head Office
Stewartby
Bedford
MK43 9LZ

Tel: 08705 258258
Fax: 01234 762040

www.hanson.com/uk